

# CCS Parlourtop

Surface Hardener for New Milking Parlours

## Construction Chemical Supplies

### Description

**Parlourtop** is a non metallic coloured dry shake topping for new milking parlour floors. When sprinkled and trowelled into fresh wet concrete floors, it forms a coloured, wear resistant surface, which has up to 800% better abrasion resistance than 40N concrete.

### Special Properties

- Coloured
- Abrasion resistant and durable
- Cost effective
- Non slip

### Technical Data

<b>Packaging:</b>	<b>Parlourtop</b> is supplied in 25 kg bags.
<b>Yield:</b>	One bag covers 5 sq mt of floor.
<b>Colour Range:</b>	Grey, Red, Green, Blue, Black and Natural.
<b>Abrasion Resistance:</b>	When tested on an accelerated wear machine at Aston University, it achieved an average of 0.05mm wear depth. (This compares to 0.4mm wear for 40N concrete in the same test).

<b>Storage:</b>	12 months minimum when stored in cool, dry conditions.
<b>Health and Safety:</b>	<b>Parlourtop</b> contains cement. Gloves and dust masks should be used during application. Because of the pigment contained in the material, overalls or old clothes should also be worn when applying this material.

### Method of Use

Reference should be made to the current method statement for the application of **Parlourtop** in new milking parlours.

To ensure a high standard of colour consistency, it is essential that the flooring contractor operates in as clean and protected environment as possible. The roof and walls should be in place and in wet or windy weather; no rainwater should spill onto the floor.

The concrete should be of good quality (minimum 30N) and the water content should be kept to a minimum. When the bleed water has evaporated, the material should be applied as follows:

- Apply 1 x 25kg bag over an area of 10 sq mt.
- Allow the moisture in the concrete to be absorbed by the **Parlourtop**, before trowelling with a wooden type float.
- Immediately apply a second 25 kg bag over the same 10 sq mt area and trowel as before. These 2 applications will ensure a total application rate of 5 sq mt per 25 kg bag.
- The floor can now be trowelled to whatever profile is required. Normally a fairly rough non slip finish is preferred.

- In warm weather it is important to cure the concrete. This can best be done by covering the floor with polythene for a period of approximately 48 hours.

For further information on ***Parlourtop*** contact:

**Construction Chemical Supplies**, 219 JFK Industrial Estate, Dublin 12.

**Tel:** 01 4503896 **Fax:** 01 4503298.

**E-mail:** [conchem@eircom.net](mailto:conchem@eircom.net)